



Figure 8 Aerial Cable

Lightem offers a board variety of fiber optic cable for different outdoor condition, such as central loose tube armored cable, duct armored cable, direct buried cable, steel wire armored cable, non metallic outdoor cable, ADSS cable and figure 8 Cable. Fitting most of the outdoor application environment, whatever for duct buried, direct buried or aerial cabling.

Lightem cables are using the premium quality fiber. Singlemode G652D, multimode 50/125um or 62.5/125um, OM3 and OM4 fibers are available. Lightem also offers the customization service on the fiber, colours and construction of the cables for catering different cases.

Features

- Up to 24 fibers the loose tube is centrally situated with good excess length and minimizes the influence of lateral crush
- Water blocking tape providing water tight property and UV protection
- Corrugated steel tape armored and PE outer sheath providing property crush resistance and gun shot resistance features
- Cross-section shows figure 8. Stranded wires as self supporting member providing excellent strain performance and convenient installation
- Comply to TIA/EIA568b-3 and ISO/IEC 11801

Fire Performances

General

Flame Retardant	IEC 60332-1, IEC 60332-2, IEC 60332-3, BS EN 50265, BS EN 50266
Fire Retardant	BS EN ISO 4589-3 Annex A (FT >= 280°C)
Low Smoke Capacity	IEC 61034 1/2, BS EN 50268-2 Annex B (>=60% Light Transmittance)
The Values for The Light Transmittance	BS EN 50268-2
Oxygen Index Testing Method	BS EN ISO 4589-2, ASTM D-2863
Halogen Free	IEC 60754-1/2, BS EN 50267-2-3 Annex A (pH >=4.3)

Specifications

General

Flame Rating	LSZH / FRNC*
Fiber Category	Singlemode / Multimode
Temperature Range	
Installation	-20°C to +70°C
Operation	-20°C to +70°C
Storage	-30°C to +70°C
Cable Design	
Fiber Count	up to 24
Tape	Water blocking tape
Tensile Strength Elements and/or Armouring Layer	Corrugated steel tape armor
Outer Jacket Material	Polyethylene (PE)
Outer Jacket Colour	Black
No. of Messenger	7
Messenger Material	Stranded steel

*For LSZH model only

Mechanical Characteristics Cable

			Unit
Fiber Count	2-12	12-24	
Cable Diameter	8.3	8.8	mm
Messenger Cable Diameter	5.0	5.0	mm
Cable Height	15.5	16.0	mm
Nominal Weight	195	205	kg/km
Max. Tension (Short-term)		1500	N
Max. Tension (Long-term)		600	N
Max. Crushing Resistance		1000	N/100mm ²
Bending Radius(Loadng)		20	D
Bending Radius(Without Loading)		10	D

Specifications (Singlemode)

Characteristics		G652D	G657A1	G657A2
Optical Characteristics				
Attenuation	1310nm	≤ 0.40 dB/km	≤ 0.40 dB/km	≤ 0.40 dB/km
	1383nm*	≤ 0.34 dB/km	≤ 0.35 dB/km	≤ 0.35 dB/km
	1460nm*	-	≤ 0.25 dB/km	≤ 0.25 dB/km
	1490nm*	-	-	≤ 0.23 dB/km
	1550nm	≤ 0.30 dB/km	≤ 0.30 dB/km	≤ 0.30 dB/km
	1625nm*	≤ 0.23 dB/km	≤ 0.23 dB/km	≤ 0.23 dB/km
	Attenuation vs. Wavelength	1285-1330nm*	≤ 0.03 dB/km	≤ 0.03 dB/km
Max. α difference	1525-1575nm*	≤ 0.02 dB/km	≤ 0.02 dB/km	≤ 0.02 dB/km
Dispersion coefficient	1285-1340nm	≥ -3.4 ≤ 3.4 ps/(nm · km)	≥ -3.4 ≤ 3.4 ps/(nm · km)	-
	1550nm	≤ 18 ps/(nm · km)	≤ 18 ps/(nm · km)	-
	1625nm	≤ 22 ps/(nm · km)	≤ 22 ps/(nm · km)	-
Zero dispersion wavelength		1312±12 nm	1300-1324 nm	1300-1324 nm
Zero dispersion slope		≤ 0.091 ps/nm ² · km	≤ 0.092 ps/nm ² · km	≤ 0.092 ps/nm ² · km
Typical value		0.086 ps/nm ² · km	0.086 ps/nm ² · km	0.04 ps/nm ² · km
PMD				
Maximum Individual Fibre		≤ 0.1 ps/√km	≤ 0.1 ps/√km	≤ 0.1 ps/√km
Link Design Value(M=20,Q=0.01%)		≤ 0.06 ps/√km	≤ 0.06 ps/√km	≤ 0.06 ps/√km
Typical value		0.04 ps/√km	0.04 ps/√km	0.04 ps/√km
Cable cutoff wavelength λ _{cc}		≤ 1260 nm	≤ 1260 nm	≤ 1260 nm
Mode field diameter(MFD)	1310nm	8.7-9.5 μm	8.4-9.2 μm	8.4-9.2 μm
	1550nm	9.9-10.9 μm	9.3-10.3 μm	9.3-10.3 μm
Effective group index of refraction(N _{eff})	1310nm	1.466	1.466	1.466
	1550nm	1.467	1.467	1.467
Point discontinuities	1310nm	≤ 0.05 dB	≤ 0.05 dB	≤ 0.05 dB
	1550nm	≤ 0.05 dB	≤ 0.05 dB	≤ 0.05 dB
Geometrical Characteristics				
Fiber Core Diameter		9 +/-1μm	9 +/-1μm	9 +/-1μm
Cladding diameter		125.0±0.7 μm	125.0±0.7 μm	125.0±0.7 μm
Cladding non-circularity		≤ 1.0 %	≤ 0.7 %	≤ 0.7 %
Coating diameter		245.0±7 μm	245.0±5 μm	245.0±5 μm
Coating-cladding concentricity error		≤ 12.0 μm	≤ 12.0 μm	≤ 12.0 μm
Coating non-circularity		≤ 6.0 %	≤ 6.0 %	≤ 6.0 %
Core-cladding concentricity error		≤ 0.6 μm	≤ 0.5 μm	≤ 0.5 μm
Curl(radius)		≥ 4 m	≥ 4 m	≥ 4 m
Delivery length		2.1 to 50.4 km/reel	2.1 to 50.4 km/reel	2.1 to 50.4 km/reel

*Attenuation loss of barefiber

Specifications (Multimode)

Characteristics		62.5/125 (OM1)	50/125 (OM2)	OM3/OM4	OM5
Geometry Characteristics					
Core Diameter		62.5±2.5 μm	50±2.5 μm	50±2.5 μm	50±2.5 μm
Core Non-circularity		≤ 5.0 %	≤ 5.0 %	≤ 5.0 %	≤ 5.0 %
Cladding Diameter		125.0±1.0 μm	125.0±1.0 μm	125.0±1.0 μm	125.050±1.0 μm
Cladding Non-circularity		≤ 1.0 %	≤ 1.0 %	≤ 0.6 %	≤ 0.6 %
Coating Diameter		245±7 μm	245±7 μm	245±7 μm	245±7 μm
Coating/Cladding Concentricity Error		≤ 10.0 μm	≤ 10.0 μm	≤ 10.0 μm	≤ 10.0 μm
Coating Non-circularity		≤ 6.0 %	≤ 6.0 %	≤ 6.0 %	≤ 6.0 %
Core/Cladding Concentricity Error		≤ 1.5 μm	≤ 1.5 μm	≤ 1.0 μm	≤ 1.0 μm
Delivery Length		up to 17.6 km/reel	up to 17.6 km/reel	up to 8.8 km/reel	up to 8.8 km/ reel
Optical Characteristics					
Attenuation	850nm	≤ 3.5 dB/km	≤ 3.5 dB/km	≤ 3.5 dB/km	≤ 3.5 dB/km
	953nm*	-	-	-	≤ 1.7 dB/km
	1300nm	≤ 1.5 dB/km	≤ 1.5 dB/km	≤ 1.5 dB/km	≤ 1.5 dB/km
Overfilled Modal Bandwidth	850nm	≥ 200 MHz · km	≥ 500 MHz · km	≥ 1500/ ≥ 3500 MHz · km	≥ 3500 MHz · km
	953nm	-	-	-	≥ 1850 MHz · km
	1300nm	≥ 500 MHz · km	≥ 500 MHz · km	≥ 500/ ≥ 500 MHz · km	≥ 500 MHz · km
Effective Modal Bandwidth	850nm	-	-	≥ 2000/ ≥ 4700 MHz · km	≥ 4700 MHz · km
	953nm	-	-	-	≥ 2470 MHz · km
10Gb/sWDM		-	-	-100/150 m	150 m
40Gb/sWDM		-	-	300/500 m	440 m
40GBASE-SR4 / 100GBASE SR10	850nm	-	-	1000/1100 m	200 m
10GBASE-SR	850nm	-	150 m	300/550 m	-
1000BASE-SR	850nm	-	750 m	1000/1100 m	-
DMD Specification					
Numerical Aperture		0.275±0.015	0.200±0.015	0.200±0.015	0.200±0.015
Group Refractive index		1,496	1,482	1,482	1,482
		1,491	1,477	1,477	1,477
Zero Dispersion Wavelength, λ ₀		1320-1365 nm	1295-1340 nm	1295-1340 nm	1297-1328 nm
Zero Dispersion Slope, S ₀		-	-	-	≤ 4(-103)/(840λ√840) ⁴) ps/nm ² · km
Zero Dispersion Slope, S ₀	1295nm ≤ λ ₀ ≤ 1310nm	-	≤ 0.105 ps/nm ² · km	≤ 0.105 ps/nm ² · km	-
	1310nm ≤ λ ₀ ≤ 1340nm	-	≤ 0.000375/(1590-λ ₀) ps/nm ² · km	-	-
	1320nm ≤ λ ₀ ≤ 1348nm	≤ 0.11 ps/nm ² · km	-	≤ 0.000375/(1590-λ ₀)ps/nm ² · km	-
	1348nm ≤ λ ₀ ≤ 1365nm	≤ 0.001(1458-λ ₀) ps/nm ² · km	-	-	-

*Attenuation loss of barefiber

Ordering Information

* Ordering Code Example

